



TECHNICAL DATA SHEET

Order reference	BM15-E
Article number	813833

Date	4-11-11	Replaces	04-03-08	No. Pages	1
-------------	---------	-----------------	----------	------------------	---

Product Description:

Style	Blanket Roll w/design printing; perforated 19 cm center & 23 cm across.
Item Size (each)	38 cm wide x 46 m long
Color	Gray Camo [Printed spunbond coverstock]
Composition	Polypropylene >98%, Surfactant < 1.0%, color pigment < 0.1 %
Structure	A trilaminate nonwoven mat of randomly oriented micro-fibers [2-10 micron diameters] contained within outer coverstocks. One coverstock is a gray lint-resistant & abrasion resistant spunbond nonwoven of continuous filaments randomly oriented and thermally point bonded [15-30 micron diameters]; the other coverstock is a lint-resistant gray meltblown nonwoven. The (3) plies are secured together with bonded dimpling.
Technology	Meltblown, Spunbond
Absorbency	Universal (Hydrophilic + Oleophilic)
Bonding	Bonded (staggered pattern) + Mechanical entanglement

Intended Application	Abrasion Resistant, Lint Resistant, & Chemical Resistant Universal Sorbent for Water-Based, Oil or Solvent Base Liquids- for various length uses.
-----------------------------	--

Absorbency Capacity	99 l per bale (saturated; medium viscosity-12.5x)
----------------------------	---

Packaging Description: (Fold and tape one corner of each roll to display printed spunbond design)

Package configuration	Case	Pkg. Weight	8.4 kg (6.7kg)
Items per Package	1-Roll / Case	Pkg. Dimensions	43cm x 43cm x 38cm H
Container type	Carton		

Physical Properties:

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002A	G/M2	384	38.4
Caliper	SPCTM-003A	mm	5.5	0.5
Absorbency** (med. Oil)	SPCTM-004B	gL/gS	12.5	2
Tensile Strength	SPCTM-007	daN	16	1.6
Color	Visual	-----	Gray + Printing	per standard

The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

**** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.