



**TECHNICAL DATA SHEET**

<b>Order reference</b>	<b>BM30X-E</b>
<b>Article reference</b>	<b>813835</b>

<b>Date</b>	4-11-11	<b>Replaces</b>	09-11-08	<b>No. Pages</b>	1
-------------	---------	-----------------	----------	------------------	---

**Product Description:**

<b>Style</b>	Blanket Roll w/design printing
<b>Item Size (each)</b>	76 cm wide x 46 m long
<b>Color</b>	Gray Camo [ <b>Printed spunbond coverstock</b> ]
<b>Composition</b>	Polypropylene >98%, Surfactant < 1.0%, color pigment < 0.1 %
<b>Structure</b>	A trilaminate nonwoven mat of randomly oriented micro-fibers [2-10 micron diameters] contained within outer coverstocks. One coverstock is a gray lint-resistant & abrasion resistant spunbond nonwoven of continuous filaments randomly oriented and thermally point bonded [15-30 micron diameters]; the other coverstock is a lint-resistant gray meltblown nonwoven. The (3) plies are secured together with bonded dimpling.
<b>Technology</b>	Meltblown, Spunbond
<b>Absorbency</b>	Universal ( <b>Hydrophilic + Oleophilic</b> )
<b>Bonding</b>	Bonded (staggered pattern) + Mechanical entanglement

<b>Intended Application</b>	Abrasion Resistant, Lint Resistant, & Chemical Resistant Universal Sorbent for Water-Based, Oil or Solvent Base Liquids- <b>for various length uses.</b>
-----------------------------	--

<b>Absorbency Capacity</b>	197 l per bale (saturated; medium viscosity-12.5x)
----------------------------	--

**Packaging Description: (Fold and tape one corner of each roll to display printed spunbond design)**

Package configuration	Case	Pkg. Weight	15.6 kg (13.6kg)
Items per Package	1-Roll / Case	Pkg. Dimensions	43 cm x 43 cm x 79 cm H
Container type	Carton		

**Physical Properties:**

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002A	G/M2	384	38
Caliper	SPCTM-003A	mm	5.5	0.5
Absorbency** (med. Oil)	SPCTM-004B	gL/gS	12.5	2
3" Tensile Strength	SPCTM-006	daN	16	1.6
Color	Visual	-----	Gray + Printing	per standard

**The above properties are "nominal" values used for PROCESS CONTROL when the product is produced and/or inspected. Performance "nominals" may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.**

**\*\* The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

<b>Attributes</b>	Product will be free of foreign material contamination, rips, holes, and tears.
<b>Labeling</b>	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
<b>Certification</b>	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.